



Product Description

Bayseal CC closed-cell spray applied polyurethane foam is a two component, medium-density, structural insulation system designed for commercial, residential, and industrial applications.

Closed-cell polyurethane foam yields a high R-value and minimizes air and moisture infiltration. The spray applied nature of Bayseal SPF systems allows for tremendous sealing properties which contributes to healthier homes and workplaces. The rigid nature of Bayseal CC increases overall structural integrity resulting in more durable structures. Bayseal CC expands during application to provide increased performance values by sealing the building envelope.

The Bayseal CC system is comprised of an "A" component or aromatic diisocyanate manufactured by Bayer MaterialScience, and a blended "B" component which includes polyols, fire retarding materials, catalysts and non-ozone depleting blowing agents.

Recommended Uses

- Walls •Unvented Attics •Ceilings
•Floors •Vented Attics •Piping
•Unvented Crawl Spaces •Vented Crawl Spaces •Foundations
•Concrete Slabs •Ducts •Tanks
•Cold Storage •Freezers •Coolers

Environmental Consideration and Substrate Temperatures

Applicators must recognize and anticipate climatic conditions prior to application to ensure highest quality foam and to maximize yield. Ambient air and substrate temperatures, moisture, and wind velocity are all critical determinants of foam quality. Extreme ambient air and substrate temperature will influence the chemical reaction of the two components, directly affecting the yield, adhesion and the resultant physical properties of the foam insulation. To obtain optimum results, Bayseal CC should be spray-applied to substrates when ambient air and surface temperatures are between 50°F and 120°F. All substrates to be sprayed must be free of dirt, soil, grease, oil and moisture prior to the application of Bayseal CC. Moisture in any form: excessive humidity (>85%R.H.) rain, fog, or ice will react chemically will adversely affect system performance and corresponding physical properties. Application should not take place when the ambient temperature is within 5°F of the dew point. Wind velocities in excess of 12 miles per hour may result in excessive loss of exotherm and interfere with the mixing efficiency of the spray gun affecting foam surface texture, cure, physical properties and will cause overspray. Precautions must be taken to prevent damage to adjacent areas from fugitive overspray.

Processing Parameters

Store at 65° to 85°F in a dry and well-ventilated area. Material in containers should be maintained at 65°F to 75°F while in use. Heated trailers, hotboxes, or heated tank storage may be necessary. Material temperature should be confirmed with a thermometer or IR gun. (continued)

Typical Physical Properties

Table with 3 columns: Properties, Test Method, Value. Rows include Fungi Resistance, R-Value (aged), Sound Transmission Coefficient, Noise Reduction Coefficient, Compressive Strength, Core Density, Closed Cell Content, Tensile Strength, Moisture Vapor Transmission (permeance), Dimensional Stability, and Air Leakage Rate.

Processing Parameters & Physical Characteristics

- Pre-heater Temperature: "A" and "B" 125-135°F
Hose Temperature: "A" and "B" 125-135°F
Pressures: 1000-1400 psi (dynamic)\*
Mix Ratio: 1 to 1 by volume "A" to "B"
Viscosity at 75°F: 400-500 cps "B" Component

Product Reactivity

- Surface Temperature: 50-120°F
Cream Time at 75°F: 2-3 seconds
Tack Free Time at 75°F: 7-8 seconds
Cure Time at 75°F: 4 hours

\*Dependent upon hose length

Test values were generated from laboratory samples and actual properties may vary with equipment and application conditions..

# Bayseal™ CC

## Credentials/Certifications

Bayseal CC is a Class I formulation, as set forth under Underwriters Laboratories ASTM E-84 (UL 723, NFPA 255, UBC Standard 8-1).

## Processing Equipment (continued)

2:1 transfer pumps are recommended for material transfer from container to the proportioner.

The plural component proportioner must be capable of supplying each component within  $\pm 2\%$  of the desired 1:1 mixing ratio by volume. Hose heaters should be set to deliver 125°F to 135 °F materials to the spray gun. These settings will ensure thorough mixing in the spray gun mix chamber in typical applications. Optimum hose pressure and temperature will vary with equipment type and condition, ambient and substrate conditions, and the specific application. Some equipment may require you to heat drums to achieve optimum material temperature. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates acceptable combinations of gun chamber size, proportioner output, and material pressures. The relationship between proper chamber size and the capacity of the proportioner's pre-heater is critical. Contact your local BaySystems representative for specific recommendations, pricing, and availability of spray and auxiliary equipment.

**CAUTION: Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.**

## Thermal Barrier

IRC and IBC codes require that SPF be separated from the interior of a building by an approved fifteen (15) minute thermal barrier, such as 1/2" gypsum wall board or equivalent, installed per manufacturer's instructions and corresponding code requirements. There are exceptions to the thermal barrier requirement:

- (1) Code authorities may approve coverings based on fire tests specific to the SPF application. For example, covering systems that successfully pass large scale tests may be approved by code authorities in lieu of a thermal barrier;
- (2) SPF protected by 1" thick masonry does not need a thermal barrier. Certain materials that offer protection from ignition, called "ignition barriers," may not be considered as thermal barrier alternatives unless they comply with NFPA 286. Applicators should request test data and code body approvals or other written indications of acceptability under the code to be sure that the product selected offers code-compliant protection.

Applicators should ensure the safety of the jobsite and construction personnel by posting appropriate signs warning that all "hot work" such as welding, soldering, and cutting with torches should take place no less than 35 feet from any exposed foam. If "hot work" must be performed all spray polyurethane foam should be covered with an appropriate fire or welder's blanket, and a fire watch should be provided.

## Vapor Retarder

Bayseal CC qualifies as a vapor retarder as defined by the International Code Council and ASHRAE (class II) at a minimum thickness of 1 inch. Building construction types with a persistent, high moisture drive require additional moisture remediation, as local building codes dictate. This is including climate zones 5 and higher in the U.S., as defined in 2004 Supplement to the IRC, Table N1101.2.

## Per Pass Application

Applicators should limit Bayseal CC thickness to 3" per pass for optimal processing and physical properties. Second passes if necessary should be applied after 10 minutes of cure time. If additional passes are needed, applicators should wait 30 minutes between passes for optimal foam processing.

## Handling and Safety

Respiratory protection is MANDATORY! Contact Bayer MaterialScience for a copy of the Model Respiratory Protection Program developed by API or visit their website at [www.polyurethane.org](http://www.polyurethane.org). Avoid contact with skin, eyes, and clothing. Open containers carefully, allowing any pressure to be relieved slowly and safely. Wear chemical safety goggles and rubber gloves when handling or working with these materials. In case of eye contact, immediately flush with large amounts of water for at least fifteen minutes, consult a physician immediately. In case of skin contact, wash area with soap and water. Wash clothes before reuse.

## Fire Hazard

Fires involving either of these components may be extinguished with carbon dioxide, dry chemical, or inert gas. Application of large quantities of water

## Surface Burning Characteristics

### ASTM Method E84 (UL 723)

	Class I
Flame Spread	≤25
Smoke Development	≤450
Nominal Thickness (Inches)	4.0

#### NOTE:

The flame spread rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

spray is recommended for spill fires. Personnel fighting the fire must be equipped with NIOSH approved self-contained breathing apparatus.

#### Cleaning of Spills or Leakage

Cover the area with an inert absorbent material such as clay or vermiculite and transfer to metal waste containers. Saturate with water but do not seal the container with the isocyanates and water mixture. The area should then be flushed with large amounts of water, in the case of the "B" component, or a 5% aqueous ammonia, in the case of the "A" component. Dispose of these materials in compliance with federal, state and local regulations.

**Caution: Isocyanates will react with water and generate carbon dioxide. This could result in rupture of closed containers.**

## Disclaimer

The data presented herein is not intended for use by nonprofessional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

All guarantees and warranties as to products supplied by Bayer MaterialScience shall have only those guarantees and warranties expressed by the manufacturer. The buyer's sole remedy as to any material claims will be against the manufacturer of the product. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. **NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE, ARE MADE BY Bayer MaterialScience WITH RESPECT TO PRODUCTS OR INFORMATION SET FORTH HEREIN.** Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Bayer MaterialScience and the manufacturer of all liability with respect to the materials and their use thereof.

**East Office**  
2400 Spring Stuebner Road  
Spring, TX 77389  
1.800.221.3626  
Tel 281.350.9000  
Fax 281.288.6450

**West Office**  
PO Box 6460  
Phoenix, AZ 85005  
1.800.289.8272  
Tel 602.269.9711  
Fax 602.269.9115

[baysystemsspray.com](http://baysystemsspray.com)



BaySystems

©2008 Bayer MaterialScience. All rights reserved.